

Approvals and conformities

RCC-M

ISO 3452-2

ALLISON ENGINES

PRATT & WHITNEY

SAFRAN

LOCKHEED MARTIN

GE

BOEING

DASSAULT AVIATION

ROLLS ROYCE

EADS

QPD-AMS 2644

PMUC (French acronym for : Products and Equipments allowed for use in Powerplants by EDF - French Electricity Bo

CFM INTERNATIONAL

MANUFACTURER: SHERWIN Inc. (USA) / NDT-Europa (NL)

DESCRIPTION / APPLICATION(S):

Type 1, method A, level 2, according AMS 2644 and ISO 3452-2, water washable fluorescent penetrant designed for detecting surface defects. (sensitivity medium)

Companion products: N120, DR-62 cleaner/ N106A, DR-60 remover
D-100, D-90G, D-106, R60 developer

DIRECTIONS FOR USE

These describe the basic process, but they may need to be amended by the user to comply with applicable specifications and/or inspection criteria provided by the contracting agency.

Application:

Apply HM-3A only to clean, dry surfaces by spraying, flowing, brushing or dipping.

Dwell-Time:

A 10 minute dwell time is suggested, although in many cases five minutes will suffice. When particularly tight cracks are suspected, or the part is especially critical, the dwell time may be extended to 30 minutes, or longer.

Do not soak the part. To increase sensitivity, as well as conserve material, allow the penetrant to drain from the part surface back into the penetrant tank.

Removal:

Use a quick, ambient temperature water wash at tap pressure to rinse HM-406 from the part surface. To avoid washing entrapped penetrant from surface flaws, do not use high water pressures and temperatures, or prolonged washing and scrubbing.

Drying:

A recirculating oven set no higher than 80°C is suggested. Leave part in oven just long enough to evaporate surface moisture. Drying is improved by using pressurized air to disperse and remove as much excess water as possible before placing part in oven.

Developing:

HM-406 is self-developing. Nevertheless it is recommended to use a developer as listed above.

Inspection:

Inspect parts under appropriate UV-A radiation (mini 1000 µW/cm² and if possible higher or equal to 1500 µW/cm²) and dimmed visible light (< 20lux), in accordance with ISO 3059.

TECHNICAL CHARACTERISTICS

- Very low halogen and sulphur content
- Compatible with all metals and certain plastics.

Appearance	green liquid
Fluorescence	green-yellow
Flash point	> 93°C
Viscosity	6,6 mm²/s ± 10% at 40°C

PRECAUTIONS FOR USE AND STORAGE

Transport / Handling: Refer to Material Safety Data Sheet (MSDS).

Storage : Keep away from moisture

Temperature range: 0°C à 50°C

Keep packaging closed after taking out some of the product.

1 Date : 04-07-2017 Written and checked by : F. Héron

This technical data sheet replaces and cancels the previous one.

1 Date : 04-07-2017 Written and checked by : F. Héron

babbco
socomore NDT

T. +33 (0)1 30 80 81 82 - F. +33 (0)1 30 80 81 99
ZI des Ebisoires - BP 136 - 15 rue des Frères Lumière - 78374 Plaisir cedex - France
www.babbco.fr - www.sherwinbabbco.eu

SHERWIN
babbco