 <p>3, av. Nagelmackers - BP 23 78450 VILLEPREUX FRANCE Pho : +33(0)1.30.80.81.98 Fax : +33(0)1.30.80.81.99 WEB : www.babbco.fr E-MAIL : sherwinbabbco@orange.fr</p>	<p>TECHNICAL DATA SHEET</p>	<p>Ref : TDS/LA-1 Page : 1/4 Rev : 2 Date : 11/09</p>
---	--	---

ALKALINE DEGREASER LA-1



MANUFACTURER : SHERWIN / NDT EUROPA

DESCRIPTION / APPLICATION(S):

Benefits:

- Compatible with all metals
- Produces very little foam
- Operates at low temperatures
- Not flammable
- Can serve as an alternative for vapour phase degreasing

The LA-1 degreasing agent has been designed specially for cleaning parts before subjecting them to penetrant testing.

It is a cleaning agent compatible with penetrants.


LA-1 degreaser agent may serve as an alternative for chlorinated solvents in vapor phase to prepare parts just before their being penetrant testing.

LA-1 is a light yellow liquid. It can be used on all metals, whether ferrous or non-ferrous, including aluminum, magnesium, nickel and titanium alloys.

It eliminates light oils such as cutting or forming oils, most light rust preventatives, and organic soils accumulated during part manufacturing. When used as a spray or for immersion with agitation, it removes grit and chips. It does not remove mineral soils such as corrosion products.

LA-1 therefore fulfils the functions of a degreasing agent in the vapour phase. It can also remove metallic and sand particles if used appropriately.

LA-1 complies with the most common requirements in terms of non-toxicity and non-corrosion, ignition point, and other parameters.

 <p>3, av. Nagelmackers - BP 23 78450 VILLEPREUX FRANCE Pho : +33(0)1.30.80.81.98 Fax : +33(0)1.30.80.81.99 WEB : www.babbco.fr E-MAIL : sherwinbabbco@orange.fr</p>	<h1>TECHNICAL DATA SHEET</h1>	<p>Ref : TDS/LA-1</p> <p>Page : 2/4</p> <p>Rev : 2 Date : 11/09</p>
---	-----------------------------------	---

It is non toxic in accordance with applicable classifications.

It contains no sodium, sulphur, chlorine, fluorine, nitrites, nor chromates, and does not corrode titanium alloys.

While having been designed primarily for use before penetrant testing, LA-1 is an excellent all purpose alkali detergent for parts subject to medium organic matter pollution.

IMPORTANT NOTE:

Before penetrant testing, you must:

- **Perfectly clean the surface of the part and the inside of the discontinuities from pollutants,**
- **Ensure that degreasing product leaves no residue.**

Actually, a number of alkali detergents leave a very hard deposit that adheres strongly to the parts after rinsing; this is **obviously a situation which is incompatible with further penetrant testing.**


LA-1 has been actually designed so as not to leave any traces on parts.

LA-1 advantages :

- Penetrant compatible
- Compatible with all metals, including aluminum, magnesium, nickel and titanium alloys.
- No chromate, chlorine, sulphur, or sodium salts.
- Low foaming.
- Free rinsing.
- Can be used with air or mechanical agitation.
- Effective at low concentrations.
- Lower materials costs compared to vapour degreasing.

PACKAGING/TRANSPORT/STORAGE :

- . Packaging : 10L, 60L
- . Transport / Handling : refer to MSDS (material safety data sheet)
- . Storage / Shelf life : 24 months.

 <p>3, av. Nagelmackers - BP 23 78450 VILLEPREUX FRANCE</p> <p>Pho : +33(0)1.30.80.81.98 Fax : +33(0)1.30.80.81.99 WEB : www.babbco.fr E-MAIL : sherwinbabbco@orange.fr</p>	<p>TECHNICAL DATA SHEET</p>	<p>Ref : TDS/LA-1</p> <p>Page : 3/4</p> <p>Rev : 2 Date : 11/09</p>
--	--	---

INSTRUCTIONS :

LA-1 is used either by spraying or by immersion.

1. **APPLICATION**

1.1. **Spray:**

Dilute the LA-1 at 3-5 % volume/volume in water, in a recirculation spray system. Although LA-1 is already effective at room temperature, working between 50 and 60° C, at a pressure of 1.5 to 2.5 kg/cm² gives even better results. Contact time should be 1 to 2 minutes. Rinse in accordance with paragraph 2.

1.2. **Immersion:**

Dilute at 10-20 % in water. Place in a mechanically or air agitation tank. The ideal temperature is 50 to 60°C. (120 to 140°F)

Immersion time depends on the type and degree of impurities.

Experience will lead to defining the optimum immersion time. Allow the parts to drain over the tank to minimize drag-out before rinsing.

Rinse in accordance with paragraph 2.

2. **RINSING**

Thoroughly rinse the parts with water, either by spraying or by immersion in an agitated tank with overflow. Water temperature shall be between room temperature and 60°C (140°F); warm water is preferred.


Rinse sufficiently to remove all cleaner/soil contamination from the surface. Do not allow cleaner to dry on the surface.

Thorough rinsing is absolutely mandatory.

In some cases, preferably use demineralised water.

3. **DRYING**

Thoroughly dry before applying the penetrant. Drying should not only result in the evaporation of surface water, but also in that of the water enclosed in the discontinuities. A recirculating drying oven is recommended whenever LA-1 is used as a degreasing agent before penetrant testing.

 <p>3, av. Nagelmackers - BP 23 78450 VILLEPREUX FRANCE Pho : +33(0)1.30.80.81.98 Fax : +33(0)1.30.80.81.99 WEB : www.babbco.fr E-MAIL : sherwinbabbco@orange.fr</p>	<p>TECHNICAL DATA SHEET</p>	<p>Ref : TDS/LA-1</p> <p>Page : 4/4</p> <p>Rev : 2 Date : 11/09</p>
---	--	--

4. SOLUTION MAINTENANCE

It is preferable to restore the adequate LA-1 concentration regularly, so as to have more consistent results over time. A concentration procedure is available.

LA-1 can absorb large quantities of pollutants. However, from time to time, the used bath should be replaced with a new one. Check with local authorities regarding waste treatment.

IMPORTANT:

When the LA-1 solution is not agitated, an apparently oily film may form on the surface.

This is not oil: do not remove it. It is an essential element of the formulation and you would reduce the effectiveness of **LA-1** if you did remove it.

HEALTH AND SAFETY : refer to MSDS.

The information given herein is given in good faith to our customers for the sole purpose of assisting them in the use of the products. The document contains no formal or implicit guarantee regarding its use.

Babb Co cannot be held responsible for damages of any nature resulting from information provided in this document. In addition, none of the information which the document contains should be interpreted as a recommendation for the use of the products which would infringe the protected rights of industrial property.